



HAISHA Paints PU Enamel Ultra Gloss is a specially designed PU-based enamel which provides an ultra-gloss finish and protects the surface for years to come

BENEFITS



Superior Hiding - High quality pigments give superior hiding thereby enhancing the finish of the applied paint.



Fast Drying - Specially designed PU formulation helps paint film to dry fast and complete the job faster.



Gloss Retention - Durable high binding paint film protects the surface and helps to keep gloss intact.

PRODUCT FEATURES

SURFACE

INTERIOR
EXTERIOR

SHADES

WHITE PLUS READY SHADES

FINISH

ULTRA GLOSS

PACKS



Shelf life: 36 months from the date of Mfg when stored in the sealed original container.

COVERAGE

1 Coat: 175-200sqft/lit **
2 Coat: 90-100sqft/lit**

**Actual coverage and drying time may vary from the quoted coverage due to factors such as surface condition, method of application.

AREAS OF APPLICATION

Metal & Wood.

-HOW TO APPLY-

A) Pre-Painting Steps

- Clean the surface using solvent/thinner to remove greasy deposits, fine particles, and dust.
- Wipes clean the surface and apply an appropriate primer to prime the surface.
- Surface imperfection / dents may be filled with suitable appropriate fillers.

B) Application Process

APPLICATION	PRODUCT CODE	THINNER	DILUTION %	APPLICATION VISCOSITY*	RECOATING PERIOD*
SANDING Sand the surface with Sandpaper 180 and wipe clean					
Metal Primer (Metal & Wood)/ Wall Primer (Solvent Thinnable)/Wood Primer (Wood)		MTO	5-10% Depending on application Consistency	Brush 30-40	6-8 Hours
Knifing Paste Filler (Wood/Metal & Wood), Wall Putty (Masonry)			Based on requirement	Supply Consistency	6-8 Hours
SANDING Sand the surface with Sandpaper 320 and wipe clean					
Metal Primer (Metal & Wood)/ Wall Primer (Solvent Thinnable)/Wood Primer (Wood)		MTO	5-10% Depending on application Consistency	Brush 30-40	6-8 Hrs
SANDING Sand the surface with Sandpaper 320 and wipe clean					
HAISHA Paints PU Enamel Ultra Gloss 1st Coat (Brush/Roller)		MTO	8-10%	Brush 55-60	6-8 Hrs
HAISHA Paints PU Enamel Ultra Gloss 2nd Coat (Brush/Roller)		MTO	8-10%	Brush 55-60	6-8 Hrs

*Viscosity as measured through a Ford Cup.

*Recoating period is quoted for 25°C and 50% Relative Humidity, these may vary under different conditions.

Ensure Metal & Wood surface is free from oil, grease and rust before paint application.



HOW TO CHOOSE COLORS

HAISHA Paints PU Enamel Ultra Gloss Shade card



*These shades are reference purpose only.

ADDITIONAL INFO

Post painting care

- For the best performance of the paint, ensure proper washing and cleaning of all algal and fungal growth at regular intervals of six months.

Precautions

- This product is flammable
- Do not apply when ambient temperature is less than 10°C or if

the temperature might drop to this level within 4 hrs of application.

- Do not over-thin or overextend the brush.
- Stir thoroughly before use.
- Incase, if settling is noticed, homogenize the material by mixing and use.

TECHNICAL DETAILS

1

DRYING TIME (@ 30°C / 50-60% R.H.)

Surface dry (15-25 mins)

2

SHEEN LEVELS

90 at 60 deg GH

3

FLASH POINT IS101/1987 PART 1 SEC 6

>30°C

4

STABILITY OF THINNED PAINTS

To be used within 24 hours



SAFETY FEATURES

Kindly refer to the MSDS for HAISHA Paints PU Enamel Ultra Gloss which gives detailed information on safety measures while handling the paint, which is available on request.

Store the container with lead in an upright position, in a cool, dry place.

Keep out of reach of children and away from eatables.

Wear eye protection during application. In case of contact with eyes, rinse immediately with plenty of water and seek medical advice.

In case of skin contact wash the skin with soap and plenty of water. Get medical attention if irritation develops or persists.

Do not breath vapour or spray. It is recommended to wear a suitable nose mask during sanding and surface preparation to avoid dust inhalation.

Do not pour leftover paint down the drain or in water courses.

No added lead, Mercury or Chromium compound.

Emerging India Division, ramkrishna mandir road, post box no. 17411, andheri (e) mumbai 400059 india
Tel 18002666066 • fax +91-22-2835 7008 • website : www.haishapaints.com • e-mail : csc@pidilite.com • toll free no. 1800 22 5502

DISCLAIMER : WHILE THE COMPANY GUARANTEES ITS PRODUCTS AGAINST DEFECTIVE MATERIALS, THE USE AND APPLICATION OF THESE PRODUCTS ARE MADE WITHOUT GUARANTEE SINCE THE CONDITIONS OF THEIR APPLICATION ARE BEYOND ITS CONTROL. IT IS RECOMMENDED TO VERIFY WITH THE COMPANY THAT THE PRODUCT IS SUITABLE FOR THE INTENDED USE, AND THAT THIS DATA SHEET VERSION IS THE LATEST ONE. THE COMPANY MAY MODIFY IT WITHOUT PRIOR NOTICE. TECHNICAL CHARACTERISTICS ARE LISTED FOR GUIDANCE ONLY. FOR MORE INFORMATION, PLEASE CONTACT THE COMPANY OFFICE IN YOUR LOCATION.